



### Rubberized Coating

**Rubberized Coating** is a solvent reduced rubberized coating formulated to dry quickly, retain flexibility and provide a textured appearance. The film is black and extremely flexible and UV resistant. It can be topcoated if required with an automotive type finish.

#### LABRATORY DATA

#### PHYSICAL PROPERTIES

• Flash Point	-4°F
• Density, Weight/Gallon @ 77°F	7.8 lbs./gallon
• Non-Volatile % by Weight	37-41%
• Non-Volatile % by Volume	31-35%
• Color	Black
• Odor	Petroleum Solvent
• Viscosity, Brookfield RVF #5 Spindle @ 10 rpmv	7,000 – 15,000 cps
• Handling Time	1 Hour
• Volatile Organic Content (VOC)	4.8 lbs./gallon
• Recommended DFT	8-10 mils
• Gravelometer (SAE J400) @ Room Temperature	8 Very Good
• @ -20F	7 Very Good





## RUBBERIZED COATING

### Accelerated Corrosion Tests

5% Salt Spray ASTM** B-117 @ Recommended DFT (2x4x1/8 in. Polished Steel Panels)	800 Hours
100% Relative Humidity ASTM D-1748 @ Recommended DFT (2x4x1/8 in. Polished Steel Panels)	1000 Hours
UV Resistance	500 Hours

## RUBBERIZED COATING

### APPLICATION PROCEDURES

#### Surface Preparation

The maximum performance of Rubberized Coating can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. UCIAC recommends that the metal substrate temperature be 50-95°F (10-35°C) at the time of product application.

#### Application

Rubberized Coating is formulated to be used as supplied. Ensure uniform consistency prior to use. Continued stirring is generally not required. If the product thickens due to cold storage or loss of solvent during use, contact UCIAC. DO NOT THIN Rubberized Coating. Incorrect thinning will affect film build, dry time and product performance. UCIAC recommends that the ambient and product temperature be 50 - 95 F (10 - 35 C) at time of application. Rubberized Coating can be airless spray applied. DO NOT FREEZE Rubberized Coating.

Undercoating-In-A-Can, Provided exclusively by:

Undercoating In A Can • [www.undercoatinginacan.com](http://www.undercoatinginacan.com) • 1-570-822-1152





**RUBBERIZED COATING**

## **APPLICATION PROCEDURES**

### **Removal**

Rubberized Coating can be removed with toluene or xylene, vapor degreasing, hot alkaline wash, or low pressure steam. Rubberized Coating can be removed from fabrics by normal dry cleaning procedures. Avoid the use of chlorinated or highly aromatic solvents when removing from painted surfaces, as these solvents may adversely affect paint.

### **Storage**

Store Rubberized Coating at temperatures between 50-95°F (10-35°C). Mild agitation is recommended prior to use.

### **Caution**

Adequate ventilation is required for cure and to ensure against formation of a combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT, OR TORCHES. Refer to Daubert's Material Safety Data Sheet for additional handling and first aid information.

**Note:** The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than UCIAC's recommended product is required, written authorization must be obtained from UCIAC.

### **CAUTION:**

The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

### **WARRANTY:**

UCIAC warrants all products manufactured by it to be free from defects in material and workmanship. UCIAC MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY UCIAC. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or a contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to UCIAC. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL UCIAC BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No UCIAC representative or other person is authorized to change this warranty in any way or to assume for UCIAC any other liability in connection with the sale or use of its products.

**Undercoating-In-A-Can**, Provided exclusively by:

Undercoating In A Can • [www.undercoatinginacan.com](http://www.undercoatinginacan.com) • 1-570-822-1152

